



Polyamide wax slurry

Better BK-3010

Product features :

Better BK-3010 is a polyamide wax slurry pre dispersed in the solvent, which can provide the anti sinking property of pigments and fillers in the paint system and the anti sagging property during paint construction.

Physical Property:

product type	Rheological additives
Appearance	Yellowish soft wax solid
relative density (water=1) 20℃	$0.88 \pm 0.03 \text{g/ml}$
Solid content	$20 \pm 1\%$
Storage period	12 months
Storage mode	Store indoors in good ventilation, away from light and heat. Storage temperature: 5-40 °C

Amount added and method of use :

- Addition amount: 0.5-2.0% of the total formula amount.
- BK-3010 needs a certain dispersion time to form the required thixotropic structure.
- High speed disperser is the most appropriate disperser. The dispersion time should be controlled within 60 minutes, and the temperature should be controlled below 50 °C.
- Better BK-3010 requires a certain dispersion time to form the required thixotropic structure.
- Better BK-3010 can be diluted again in advance to facilitate addition and dispersion.
- If the surface of Better BK-3010 is dry, skinned, caked, etc., this part needs to be removed.

Safe operation information :

- Transportation and storage: It must be transported and stored at a temperature of 5-40 °C. Store in a cool, dry and ventilated place and keep upright to prevent leakage. Keep away from heat sources and ignition sources

- during storage, transportation, loading and unloading. Containers containing products shall not be directly exposed to thermal radiation.
- This product contains solvent and must be handled with care to avoid contact with skin and eyes. For more details, please refer to MSDS.
- The above information is based on the experimental data of our company. The performance may be different when the base material and construction conditions are different. It is recommended that customers try it according to their own conditions.

matters needing attention:

In case of poor recoating during baking and drying, especially in alkyd amino baking varnish, attention must be paid